

# MOLYKOTE<sup>®</sup> S-1010

## Anti-Spatter Spray

Water-based translucent coating that avoids sticking of spots on welding tools and parts

### Features

- Water-based
- Allows posterior painting of the welded parts
- Easy removal by water-cleaning

### Applications

Water-based anti-spatter spray for welding applications.

### How to use

Spray onto parts that need protection prior to welding.

### Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

### Usable life and storage

When stored at or below 20°C (68°F) in the original unopened containers, this product has a usable life of 60 months from the date of production.

### Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE<sup>®</sup> sales office or MOLYKOTE<sup>®</sup> distributor.

### Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE<sup>®</sup> sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Color		Transparent
	Service temperature range	°C	0 to +100
DIN 51562	Viscosity at 40°C	mm <sup>2</sup> /s	<50

<sup>(1)</sup>DIN: Deutsche Industrie Norm.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 2000-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.