

MSP TR
Adhesive/Sealant Capabilities
Transparent MSP

Tecnite[®]
innovative solutions

Application Possibilities

Based upon silyl modified polymer Tecnite MSP TR is a one component transparent MS-Polymer solution for:

- Multipurpose interior DIY applications
- Elastic bonding/sealing applications

Features

- Solvent, isocyanate and silicone free
- Odourless neutral fast cure
- Very good aging properties
- Permanent elasticity for temperatures between -40 to +100C
- Will not discolor when exposed to indirect UV

Typical Product Data - Tecnite MSP TR

	Unit	Value
Base Material		SMP
Curing Method		Absorption of moisture from the air
Specific Gravity	g/ml	ca. 1.0
Shelf Life (5-25°C) (*)	Months	12

(*) Please refer to production data on the original container.

Process Data

	Norm	Value
Skin Forming Time	20°C/50% R.H.	10-15 minutes
Curing Speeds	after 24 hours	ca. 2 mm
Application Temperature		+5 to +35°C
Volume Change / Shrinkage	DIN 52451	< 3%

DISTRIBUTORS GROUP EUROPE

Handelsweg 6, NL- 2404 CD Alphen aan den Rijn, The Netherlands
Tel. 0031-172-436361 Fax 0031-172-420310
info@dge.nl www.dge-europe.com



Cured System Data - Tecnite MSP TR

	Norm	Unit	Value
Shore A Hardness	DIN 53505	Shore A	ca. 38
Tensile Stress	DIN 53504/ISO 37	M Pa	1.0
Tensile Stress at Break	DIN 53504/ISO 37	M Pa	2.2
Elongation at Break	DIN 53504/ISO 37		250%
Temperature Range in Service		°C	-40 to +100
Standard Color			Transparent

Adhesion Capabilities

Tecnite MSP TR adheres well without primer on non-porous substrates of glass, aluminium, metals, plastics, ceramics, etc., which are clean, dry, dust and grease free. The use of a "wash" primer for degreasing the substrate's surface is recommended when high adhesion levels are needed due to great thermal or physical loads and specifically when wet conditions are the norm. It is advisable to use primers on untreated wooden surfaces as well as porous surfaces of brick, cement etc. No adhesion on untreated polyethylene, polypropylene and Teflon.

For more details concerning our range of primer's capabilities on substrates not mentioned here please consult your local technical sales support team as testing may be advisable.

Method of Use

Tecnite MSP TR can easily be extruded with a hand or air pressure gun at temperatures between +5C and +35C. For bonding applications the substrates need to be assembled within 10 minutes after applying Tecnite MSP TR. For sealing applications Tecnite MSP TR should also be tooled or smoothed within 10 minutes. In general an adhesive thickness of 2 mm is recommended.

Shelf Life Information

Tecnite MSP TR may be stored for 12 months in its original unopened container. Product needs to be stored in a dry cool area in temperatures ranging from +5 to +25C.

Package Types Available

- | | | | |
|--------------|--------|---------|-----------|
| - Cartridges | 290 ml | - Pails | 18 liter |
| - Sausages | 600 ml | - Drums | 190 liter |

Health and Safety

The user is cautioned to avoid skin and eyes contact with the products. If eye contact occurs, immediately flush eyes with large amounts of water for at least 15 minutes and secure medical attention. If skin contact occurs, wash affected area thoroughly with soap and water.

For additional information on this product's hazards and recommended precautions please refer to the relative product material safety data sheet.

The information contained in this technical data sheet is to the best of our knowledge correct. However, by no means can it be considered a guarantee as usage, working area and application of the product in accordance with the instructions given and their success in application, is beyond our control and is dependent on a number of factors. We decline any responsibility for the improper use of the product as the application recommendations contained herein are to be considered only as a general guideline. If at all in doubt, preliminary tests should be carried out.

DISTRIBUTORS GROUP EUROPE

Handelsweg 6, NL- 2404 CD Alphen aan den Rijn, The Netherlands
 Tel. 0031-172-436361 fax 0031-172-420310
 info@dge.nl www.dge-europe.com

